

DATA SHEET**SL CAST 90****General product information**

Solvent free elastic two component polyurethane *casting resin* with good temperature properties and low pouring viscosity. **SL CAST 90** is designed as a casting for embedding of Fiber Optic Traffic Sensors and works also well as loop sealant.

Typical properties at 20 °C

	Polyol SL CAST 90-POL	Polyisocyanate SL CAST 90-ISO	Mixture
Density [g/cm³] DIN 53217/2	1.20	1.20	1.20
Viscosity [mPa·s] DIN 53018/1+2	3500	300	1400
Mixing ratio by weight	100	33	-

Colour: black

Potlife: from 2 till 13 minutes possible

Curing profile

Curing time depends on the potlife, material temperature and ambient temperatures. The ambient temperature should not fall below +5°C during curing.

Typical values of cured casting

Shore hardness	35 D / A 90	DIN 53505
Tensile strength	11.0 N/mm ²	DIN 53455
Elongation at break	250 %	DIN 53455
Tear resistance	20 N/mm	DIN 53356

Processing Conditions

The resin component should be stirred well before using. The processing is done by preference with a two component metering and mixing machine. These machines enable a working with short potlives. The parts to be glued should be clean, dry and free from grease.

Precaution

Material safety data sheets SL CAST 90-ISO and SL CAST 90-POL should be read very carefully before use.

Packaging

3 Kg units. Others size on request.

Storage life

Both components must be protected against humidity. Do not store at temperature below + 5 °C. 15 - 20 °C is the most favourable storage temperature. Original closed units can be stored for at least 6 months at ambient temperature. After a long storage period, the resin component should be stirred well before using.

Notice

The information herein is based on our present experience and is believed to be correct. Notice of legal requirements and existing patent rights has to be taken.

Important notes:

Our advice in connection to technical applications either verbal, written or by means of experiments are given in good faith and to the best of our knowledge as an indication without obligation also in respect of third party protection. This does not dismiss the users obligation to check that the supplied product is suitable for the desired purpose and that the necessary precautionary measures have been taken. Application, use and processing of our products take place outside our control possibilities. They are therefore the responsibility of the end user. We kindly refer you to our standard sales conditions. As our data sheets are regularly updated, please check your files to confirm you have the current edition. It is sometimes useful to perform application tests or to develop special variations for certain projects.

For more specific information please contact our Technical Department.

Sensor Line - Gesellschaft für optoelektronische Sensoren mbH
Carl-Poellath Straße 19, D-86529 Schrobenhausen, Germany
Tel.: +49 (0) 8252 / 8943-0, Fax: +49 (0) 8252 / 8943-11